

CRG Bearings



■ Material structure

Sliding layer: Continuous wound PTFE and high-strength fibers encapsulated in an internally lubricated, high-temperature and high-strength filled epoxy resin.

Backing: Continuous wound glass fiber encapsulated in high-strength epoxy resin.

Technical data

Material properties	Standard	Unit	CRG
Density	ISO1183	g/cm ³	1.90
Max. water absorption	ISO62	%	0.1
Max. PV (dry)	ITS026	N/mm ² ×m/s	1.5
Coefficient of friction	ITS025	μ	0.03~0.12
Long-term application temperature	ITS029	°C	+160
Short-term application temperature	ITS029	°C	+180
Lowest application temperature	ITS029	°C	-196
Max. Speed	ITS032	m/s	0.13
Compressive strength	ITS033	MPa	420
Max. static load	ITS027	MPa	240
Max. dynamic load	ITS028	MPa	160
Linear coef. of thermal Expansion (25 ~ 150°C)	ISO11359	10 ⁻⁶ ×K ⁻¹	13

*ITS: CSB company's internal test standards.

**Test temperatures are 23°C unless otherwise stated.

Typical features

For high load oscillation and rotation applications

Excellent wear resistance

Very good chemical resistance

Low friction coefficient

Oil forbidden



Typical applications

Hydraulic cylinder pivots

Boom lifts, scissor lifts

Cranes, material handling equipment

Construction machinery arm bushes

Port machinery